


HT01-0250 250 GALLON HOLDING TANK HT01-0300 300 GALLON HOLDING TANK PRODUCT INFORMATION

General Overview

These unique portable holding tanks eliminate the use of threaded and solvent-cemented conventional plumbing fittings, which are usually discarded after each use. The 3" (7.6cm) ports utilize "Fernco"[®] flexible rubber couplings, which are available in a variety of pipe sizes and plumbing configurations such as couplers, elbows, tees and caps. These flexible fittings are re-usable. Two sizes of tanks are available. These durable plastic polyethylene tanks are supplied with the top, centre port #4, cut open with a 3" rubber cap and clamp provided. Other ports can be cut open and a rubber cap and clamp supplied at the customer's request for a nominal fee.



REQUIRED TOOLS TO PLUMB TANKS TO SEWAGE CONNECTION: A SLOTTED SCREW DRIVER OR 5/16" HEX HEAD NUT DRIVER, 3" HOLE SAW AND HAND SAW

POLYJOHN USA

PolyJohn Enterprises Corp 2500 Gaspar Ave. Whiting, IN 46394 Phone: 800-292-1305 Fax: 219-659-0625 www.polyjohn.com info@polyjohn.com


POLYJOHN WORLDWIDE

PolyJohn (UK) Ltd. Equinox 1 Audby Lane Wetherby, England LS22 7RD Phone: 44 (0) 1937-583333 Fax: 44 (0) 1937-583322 sales@polyjohn.co.uk

> HT01-0250/0300 Info July 2008 Page 1 of 4


POLYJOHN CANADA

PolyJohn Canada P.O. Box 2300 199 Forest Plain Rd. Orillia, Ontario LV3 652 Phone: 800-465-9590 Fax: 705-325-8250 info@polyjohncanada.ca



HT01-0250 TANK WEIGHT 110 LBS. (49.5kg) EMPTY CAPACITY 250 GALLONS PORT #4 IS OPEN & SUPPLIED WITH CAP & CLAMP

QUANTITY	PORT #1	PORT #2	PORT #3	PORT #4	PORT #5	PORT #6
				X		
				X		
				X		
				X		
				X		
				X		



HT01-0300 TANK WEIGHT 130 LBS. (58.5kg) EMPTY CAPACITY 300 GALLONS PORT #4 IS OPEN & SUPPLIED WITH CAP & CLAMP

QUANTITY	PORT #1	PORT #2	PORT #3	PORT #4	PORT #5	PORT #6	PORT #7	PORT #8
				Х			*	*
				Х			*	*
				Х			*	*
				Х			*	*
				Х			*	*
				Х			*	*



HT01-0250 250 Gallon Holding Tank HT01-0300 300 Gallon Holding Tank TECHNICAL INFORMATION

Resin Physical Properties

All holding tanks are manufactured using a linear, low density polyethylene, hexene copolymer resin and are made by the rotational molding process. The resin has excellent processabilities, outstanding dimensional control, low warpage, excellent environmental stress crack resistance (ESCR) and long term, ultraviolet (UV) stabilization. The resin and pigments used for coloring are FDA food grade compliant.

The nominal wall thickness for these tanks is 0.250". Due to the manufacturing process, wall thickness may vary.

These tanks are supplied with one Fernco[®] flexible ruubber coupling cap and one port open. The outlet ports are designed to be used with Fernco[®] flexible rubber couplings. These couplings are manufactured from tough, elastomeric polyvinyl chloride (PVC). They are unaffected by soil conditions and resistant to chemicals, ultraviolet rays, fungus growth and normal sewer gasses. The clamps, band screw and housing are made from Series 300 stainless steel.

RESIN PHYSICAL PROPERTIES	TEST METHOD	UNITS	TYPICAL VALUE
Melt Index	ASTM D-1238	g/10 min.	5.2
Density	ASTM D-4883 or	g/cm ³	0.932
	ASTM D-1505		
Melting Point	ExxonMobil	°C (°F)	125 (257)
-	Method	. ,	

MOULDED PROPERTIES	TEST METHOD	UNITS	TYPICAL VALUE
Tensile Strength at Yield	ASTM D-638	Mpa (psi)	15.1 (2200)
Tensile Break Elongation	ASTM D-638	%	750
Flexural Modulus	ASTM D-790	Mpa (psi)	600 (87,000)
1% Secant	Procedure B		
Impact Strength @ -40°C	ARM **	J (ft-lb)	
1/8" (3.17 mm) thickness			88 (65)
1/4" (6.35 mm) thickness			217 (160)
Environmental Stress Crack	ASTM D-1693	hr	
Resistance (ESCR), F50	Condition A		
	100% Igepal		>1000
	10% Igepal		650
Deflection Temperature	ASTM D-1693	°C (°F)	
@A33 66 psi (455 Kpa)			55 (131)
@264 psi (1820 Kpa)			37 (98)